

**AMENDMENTS TO THE CLAIMS WITH MARKINGS TO SHOW CHANGES MADE,
AND LISTING OF ALL CLAIMS WITH PROPER IDENTIFIERS**

1. (Currently amended and withdrawn) A hydraulic binder, comprising:
 cement as main constituent;
 a mixture of a chromate reducer and a carrier material added to the cement,
 wherein the chromate reducer contains two iron(II) sulfate components, with a first
 component made of filter salt obtained during titanium dioxide production, and with
 a second component being ~~green-salt~~ copperas; and
 a mineral acid regulator added to the chromate reducer.
2. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the
 mineral acid regulator is added to the filter salt.
3. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the
 mineral acid regulator is ground limestone.
4. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the
 mineral acid regulator is added at an amount between 3.0 weight-% and 18
 weight-% in relation to the amount of filter salt.
5. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the
 first component and the second component are mixed at a ratio of 1:1 to 1:5.
6. (Previously presented and withdrawn) The hydraulic binder of claim 1, further
 comprising a hydrophobic substance in the form of polymeric alcohols for addition
 to the mixture.

7. (Previously presented and withdrawn) The hydraulic binder of claim 6, wherein the polymeric alcohols are made on the basis of plastic or cellulose, in granular or liquid form.
8. (Previously presented and withdrawn) The hydraulic binder of claim 1, further comprising a hydrophobic substance in the form of a siloxane for addition to the mixture.
9. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the carrier material is a silica gel.
10. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the carrier material is activated alumina.
11. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the carrier material is dry sand at a particle size between 0.1 mm and 0.4 mm.
12. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the carrier material is a catalyst powder.
13. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the carrier material in the mixture is at an amount between 5 weight-% and 15 weight-% in relation to the amount of chromate reducer.
14. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the mixture is present at an amount between 0.01 weight-% to 5.0 weight-% in relation to a content of cement.

15. (Currently amended) A chromate reducer, comprising a mixture of two iron(II) sulfate components and an acid regulator, with a first iron(II) sulfate component being filter salt obtained during titanium dioxide production, and a second iron(II) sulfate component being ~~green-salt~~ copperas.
16. (Previously presented) The chromate reducer of claim 15, wherein the acid regulator is a mineral acid regulator.
17. (Previously presented) The chromate reducer of claim 15, wherein the acid regulator is present at an amount between 3 weight-% and 18 weight-%, in relation to the amount of filter salt.
18. (Previously presented) The chromate reducer of claim 15, the first component and the second components are mixed at a ratio of 1:1 to 1:5.
19. (Currently amended and withdrawn) A method of reducing the content of water-soluble chromate in cement, comprising the steps of:
preparing a mixture of iron(II) sulfate in the form of filter salt obtained during titanium dioxide production and iron(II) sulfate in the form of ~~green-salt~~ copperas and a mineral acid regulator to produce a chromate reducer ~~[[for]]~~; and
adding the mixture to cement.
20. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the mineral acid regulator is added at an amount between 5 weight-% and 15 weight-% in relation to the amount of filter salt.
21. (Previously presented and withdrawn) The hydraulic binder of claim 3, wherein the limestone has a particle size of 0 mm to 2 mm.

22. (Previously presented and withdrawn) The hydraulic binder of claim 8, wherein a content of the hydrophobic substance in the mixture ranges between 0.5 weight-% to 10 weight-%.
23. (Previously presented and withdrawn) The hydraulic binder of claim 8, wherein a content of the hydrophobic substance in the mixture ranges between 1 weight-% and 5 weight-%.
24. (Previously presented and withdrawn) The hydraulic binder of claim 1, wherein the mixture is present at an amount between 0.2 weight-% and 1 weight-% in relation to a content of cement.
25. (Previously presented) The chromate reducer of claim 15, wherein the acid regulator is ground limestone.